

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 111 078 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
27.06.2001 Bulletin 2001/26

(51) Int Cl.7: **C22C 21/00**

(21) Application number: **00311378.4**

(22) Date of filing: **19.12.2000**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **22.12.1999 US 469858**

(71) Applicant: **UNITED TECHNOLOGIES
CORPORATION
Hartford, CT 06101 (US)**

(72) Inventor: **Watson, Thomas J.
South Windsor, Connecticut 06074 (US)**

(74) Representative: **Hall, Matthew Benjamin
Frank B. Dehn & Co.
179 Queen Victoria Street
London EC4V 4EL (GB)**

(54) **High strength aluminium alloy**

(57) A high strength dispersion strengthened aluminium alloy comprising an aluminum solid solution matrix strengthened by a dispersion of particles based on the compound Al_3X , where Al_3X has an $L1_2$ structure, is de-

scribed. Various alloying elements are employed to modify the lattice parameter of the matrix and/or the particles so that the matrix and particles have similar lattice parameters. The alloy is produced by rapid solidification from the melt.

EP 1 111 078 A2

Description

[0001] The present invention relates to an aluminum based alloy having excellent mechanical properties at up to about 300° C.

[0002] Aluminum and aluminum alloys have a combination of good mechanical properties and low density that make them useful for some aerospace applications. However, most prior aluminum alloys have had a maximum use temperature of about 150°C.

[0003] Prior attempts to improve the high temperature mechanical properties of aluminum alloys have included the addition of inert particles such as alumina into an aluminum matrix. The inert particles strengthen the alloy and help it to maintain properties at elevated temperatures. However, the benefits obtained in the addition of such particles are limited and such materials have not found widespread application.

[0004] Other attempts to improve the mechanical properties of aluminum have focused on the development of stable intermetallic particles in an aluminum matrix by rapid solidification. U.S. Patent 4,647,321 is typical of such alloys. This type of alloy has generally been observed to undergo particle coarsening and resultant loss of mechanical properties during processing.

[0005] A limited number of alloys are known which contain the element scandium. One group of such alloys is typified by U.S. Patents 4,689,090 and 4,874,440, in which scandium is described as promoting or enhancing superplasticity. Superplasticity is a condition wherein, at elevated temperatures, a material displays unusual amounts of ductility and can be readily formed into complex shapes. Superplasticity is generally regarded as incompatible with elevated temperature strength and stability.

[0006] Another patent WO 95/32074 suggests the use of scandium to enhance the weldability of aluminum alloys. Finally, U.S. Patent 5,620,652 mentions the possible small amounts of scandium as grain refinement agents.

[0007] Other patents relating to scandium containing aluminum alloys include WO 96/10099.

[0008] None of these prior patents appear to suggest the use of scandium in an aluminum alloy for use at elevated temperatures.

[0009] According to the present invention, an aluminum alloy containing a dispersion of particles having $L1_2$ structure is described. The alloy is processed by rapid solidification. Al_3Sc is an example of an $L1_2$ compound which may be dispersed in an aluminum solid solution matrix.

[0010] According to the present invention, intentional amounts of other alloying elements are made to modify the lattice parameter of the matrix and/or the Al_3X $L1_2$ particulates; the alloying additions are selected in kind and amount so as to render the lattice parameter of the matrix and the particles essentially identical at the intended use temperature.

[0011] Both the aluminum solid solution matrix and the Al_3X particulates have face centered cubic structures, and will be coherent when their respective lattice parameters are matched to within about 1% preferably to within about .5%, and most preferably to within about .25%. When the condition of substantial coherency is obtained, the particles are highly stable at elevated temperatures, and the mechanical properties of the material will remain high at elevated temperatures.

[0012] Certain preferred embodiments of the present invention will now be described by way of example only.

[0013] The present invention includes compositional, microstructural, and processing aspects. A broad exemplary range for an alloy according to the present invention includes 3-16 wt. % scandium, 3-6 wt. % magnesium, 2-5 zirconium, and 1-4 wt. % titanium.

[0014] An alloy of aluminum containing 3-16% Sc is a model alloy for explaining this invention. A simple binary alloy consisting of aluminum and 3-16 wt. % scandium will form an aluminum solid solution matrix containing trace amounts of scandium and a dispersion of Al_3Sc particles having an $L1_2$ structure (an ordered FCC structure with Sc at the corner positions and Al on the cube faces). Such an alloy has little or no practical application at elevated temperatures because the matrix lattice parameter differs substantially from the lattice parameter of the Al_3Sc particles. In the case of a simple binary alloy, the difference in lattice parameters results in a relatively high interfacial energy at the interfaces between the matrix and the particles as well as stresses and strains relating to the lack of coherency. These factors contribute to relatively high diffusion rates at elevated temperatures and cause coarsening of the particles under conditions of stress at elevated temperature. Accordingly, such a simple binary alloy is not suited for use at elevated temperatures (greater than about 150 °C).

[0015] The present invention material solves these drawbacks by alloying additions to render the matrix and Al_3X particulate lattice parameters essentially identical.

[0016] The matrix is an aluminum solid solution whose lattice parameter has been modified by additions of one or more alloying elements selected from the group consisting of Mg, Ag, Zn, Li and Cu.

[0017] Table I illustrates the effect of 1 wt % of each of these elements on the lattice parameter of aluminum at room temperature.

Table I

Element Added	Change in Lattice Parameter
None (Pure Al)	4.049 Å°
Mg	+ 0.0052 Å°
Ag	+ 0.00002 Å°
Zn	- 0.0003 Å°
Li	- 0.0005 Å°
Cu	- 0.0022 Å°

[0018] The elements Mg, Ag, Zn, Cu and Li are utilized because they partition to the aluminum solid solution matrix, they modify the lattice parameter of aluminum, and they have high solid solubility in aluminum. The skilled artisan can use the information in Table I to estimate how much of an alloying element, or combination of elements in Table I will be required to produce an aluminum solid solution matrix with a particular lattice parameter.

[0019] Several elements form precipitates having the desired equilibrium $L1_2$ structure when added to Al. Other elements form metastable $L1_2$ structure phases when added to aluminum, their equilibrium structures may be $D0_{22}$ or $D0_{23}$.

[0020] It can be demonstrated that adding metastable $L1_2$ formers in combination with equilibrium $L1_2$ formers will produce an equilibrium $L1_2$ structure when the atomic % of the metastable $L1_2$ forming element(s) in the compound is less than about 50% of the total equilibrium $L1_2$ forming elements, and preferably less than about 25%.

[0021] Table II lists the Al_3X $L1_2$ lattice parameter at room temperature for a variety of elements; Ti, Nb, V, and Zr are metastable $L1_2$ formers. Sc, Er, Lu, Yb, Tm and U are stable $L1_2$ formers.

[0022] Since the lattice parameter of Al is less than that of the equilibrium $L1_2$ formers, it is logical to prefer that at least a portion of the "X" additions be chosen from those that form equilibrium $L1_2$ particles with the smallest lattice parameters, Sc, Er and Lu are thus preferred. Preferably at least 10% of the "X" atoms are Sc.

[0023] The volume fraction of the $L1_2$ phase is preferably from about 10 to about 70% by volume.

Table II

X	Al_3X lattice parameter, Å° @ Room Temperature
Ti	3.967 (1)
Nb	3.991 (1)
V	4.045 (1)
Zr	4.085 (2)
Sc	4.101 (3)
Er	4.167 (3)
Lu	4.187 (3)
Yb	4.202 (3)
Tm	4.203 (3)
U	4.267 (3)
Pure Al	4.049

(1) equilibrium Al_3X structure is $D0_{22}$

(2) equilibrium Al_3X structure is $D0_{23}$

(3) equilibrium Al_3X structure is $L1_2$

[0024] Because high temperature stability is desired in this alloy, it is preferred to add zirconium because zirconium has an exceptionally low diffusion coefficient in aluminum. Low diffusion coefficients predict low rates of diffusion and low rates of diffusion are desired in order to minimize particle coarsening during long exposures at elevated temperatures. Preferably at least 10% of the "X" atoms are Zr.

[0025] At 500° F. the diffusion coefficient of scandium in aluminum is about 2.9×10^{-18} . The diffusion coefficient of titanium in aluminum is about 1.3×10^{-17} at the same temperature meaning that titanium diffuses in aluminum more readily than does scandium. The diffusion coefficient of zirconium in aluminum is only 1.4×10^{-21} , meaning that the diffusion rate of zirconium in aluminum is three orders of magnitude less than the rate of diffusion of scandium in aluminum. Since zirconium forms the desired L_{12} phase (albeit metastable) in aluminum, it is preferred to add zirconium for diffusional stability. It is also preferred that at least 10% of the "X" atoms are Ti.

[0026] Chromium is another element which might be added in small quantities to improve diffusional stability, since Cr has a diffusion coefficient of about 2.3×10^{-22} at 500° F. However, chromium is not preferred because binary alloys of aluminum chromium do not form an L_{12} phase. Consequently, if chromium is added, care must be taken that the amount of chromium is low enough as not to cause the precipitation of extraneous non L_{12} phases. Chromium, if added should preferably be present in amounts of less than about 1% by weight.

[0027] In all cases, the skilled artisan will recognize the desirability of evaluating compositions after exposure at long times at elevated temperatures for the presence of extraneous phases which do not have the L_{12} structure and which may cause deleterious properties. It is broadly preferred to have less than 5 vol % of such phase, and most preferred to have less than 1 vol % of such phases.

[0028] Example alloys which are currently preferred include (by wt.):

a. 4% Sc, 11.9% Er, 3.0% Ti, 2.5% Zr, bal Al. This is a calculated composition which has been produced, but not yet evaluated. The matrix and particle lattice parameters should be essentially identical at an intended use temperature of 300°C and the alloy should contain about 30% by volume of the L_{12} phase.

b. 6% Mg, 4% Sc, 11.9% Er, 3.0% Ti, 2.5% Zr, bal Al. This is a calculated alloy composition which has been produced but not yet evaluated. The matrix and particle lattice parameters should be essentially identical at an intended use temperature of 190°C and the alloy should contain about 30 volume % of the L_{12} phase.

c. 30% Sc, 60% Mg, 3.0 % Ti, 2.5% Zr. This is a calculated alloy whose matrix and particle lattice parameters should be essentially identical at 190°C and the alloy should contain about 13 volume % of the L_{12} phase.

[0029] Extensive research has been performed for more than 50 years in the field of nickel superalloys. The majority of nickel base superalloy materials comprise a nickel solid solution, face centered cubic, matrix containing a dispersion of Ni_3Al . The Ni_3Al phase is a face centered cubic ordered phase of the L_{12} type. Nickel base superalloys maintain high degrees of strength at temperatures very near their melting point and it is generally accepted that it is desirable in nickel base superalloys for the lattice parameter of the precipitate particles to be substantially equal to the lattice parameter of the matrix phase at the use temperatures. Researchers in the field of nickel base superalloys suggests that the strength contribution of the Ni_3Al particles is due to the formation of antiphase boundaries as dislocations pass through the ordered particles.

[0030] Deformation in metallic materials occurs as a consequence of the motion of defects known as dislocations, which pass through the crystal structure in response to applied stress. In the case of ordered L_{12} particles in a face centered cubic matrix having an identical or nearly identical lattice parameter, a single perfect or unit dislocation in the matrix material can split into two partial dislocations separated by an antiphase boundary in order to pass through the ordered L_{12} particles. The energy required to split a single dislocation into two partial dislocations and to create the antiphase boundary which separates the two partial dislocations is generally believed to contribute to the strengthening which is observed in gamma/gamma prime superalloys at elevated temperature.

[0031] It is believed that the strengthening mechanism in this present invention aluminum alloys may be analogous to that which has previously been described in the generally unrelated area of nickel base superalloys.

[0032] The L_{12} particles found in the invention alloy are essentially equilibrium phases and are stable over a wide temperature range.

[0033] However, in the alloys of the present invention, the amount of scandium which is soluble in aluminum varies only very slightly from room temperatures up to temperatures in excess of 300° C. This means that Al_3Sc phase particles, for example, in the present invention are stable at elevated temperatures and that the invention alloys are thermally stable at elevated temperatures and can withstand long exposures at high temperatures. However, this also means the alloy is not particularly susceptible to heat treatment and it also means that the distribution and size of the precipitate particles is controlled by the rate of solidification from the liquid to solid states.

[0034] In order to get the fine dispersion of Al_3X L_{12} particles which is required to produce useful amounts of strengthening at elevated temperatures, it is generally necessary to solidify the invention materials from the liquid state at a rapid rate. The cooling rate required varies with the type and amount of "X" type elements present in the alloy, higher amounts of X and similar elements generally require a higher degree of cooling in order to maintain a fine dispersion.

[0035] For scandium contents of about wt%, 4%, cooling rates of about 10^5 to 10^6 °C/sec. appear to be necessary to get the required fine particle dispersion. The skilled artisan will be able to readily determine the required rate using only very limited amounts of experimentation.

[0036] It is desired that essentially all of the particles have an average size of less than about 500 nm nanometers and preferably that more than 10% of the particles have a diameter of less than 100 nm. In this invention material, the presence of larger particles will not be detrimental, especially for creep, but it will be found necessary to have a certain volume fraction of particles in the above size ranges present in order to provide the useful strength properties.

[0037] While rapid solidification is required for the manufacture of the invention material, the rate (10^4 °C to 10^8 °C/se) is important, but the particular solidification technique is not. Appropriate methods include, without limitation, gas atomization and melt-spinning. Such rapid solidification techniques generally produce powder, fibers or ribbons which must be consolidated to form useful articles.

[0038] Known consolidation techniques including vacuum hot pressing, HIPping, and extrusion of canned powder and it does not appear that any particular consolidation technique is critical to the success of the invention. However, consolidation must be performed in a vacuum or inert atmosphere in order to avoid oxidation. We believe that consolidation at temperatures between about 200° C and 500° C and pressures of about 5 to 25 ksi (34.5 to 172 Pa) for times of from 5 to 20 hours are generally appropriate. We have consolidated invention material using a blind die and punch. Other processes such as a hot rolling and extrusion may also be appropriate.

[0039] The invention alloys may be used to form components of mechanical devices, especially devices such as the compressor section of a gas turbine engine where low weight is required and temperatures on the order of 300° C are encountered.

[0040] The invention material may be used in a bulk form, it may also be used as a matrix material for composites.

[0041] Such composites will comprise the invention material (Al solid solution matrix containing coherent $L1_2$ Al_3X particles) as a matrix containing a reinforcing second phase which may be in the form of particles, whiskers, fibers (which may be braided or woven) and ribbons.

[0042] The reinforcing phase in a composite application should not be confused with the Al_3X $L1_2$ phase in the invention material. The Al_3X $L1_2$ particles will typically be less than 100 nm in diameter, reinforcing phases added to metal matrix composites usually have minimum dimensions which are greater than 500 nm, typically 2-20 μ m.

[0043] Suitable reinforcement materials include oxides, carbides, nitrides, carbonitrides, silicides, borides, boron, graphite, ferrous alloys, tungsten, titanium and mixtures thereof. Specific reinforcing materials include SiC, Si_3N_4 , Boron, Graphite, Al_2O_3 , B_4C , Y_2 and Y_2O_3 . These reinforcing materials may be present in volume fractions of up to about 20 vol %.

[0044] US patents 4,259,112; 4,463,058; 4,597,792; 4,755,221; 4,797,155; and 4,865,806 describe methods of producing metal matrix composites and these patents are expressly incorporated herein by reference.

Claims

1. An aluminum material comprising:
an aluminum solid solution matrix containing 10-70 vol % of an Al_3X phase having an $L1_2$ structure where X is selected from the group consisting of Sc, Er, Lu, Yb, Tm and U, and mixtures thereof and further containing Ti, Nb, V, Zr, and Cr in amounts insufficient to cause the formation of more than about 5 vol % of non $L1_2$ structure phases and wherein the aluminum solid solution matrix contains at least one element selected from the group consisting of Mg, Ag, Zn, Li, Cu and mixtures thereof.
2. A material as claimed in claim 1 wherein the lattice parameter of the aluminum solid solution matrix is greater than the lattice parameter of pure aluminum.
3. A material as claimed in claim 1 or 2 wherein the lattice parameter of the $L1_2$ phase is less than the lattice parameter of Al_3Sc .
4. A material as claimed in any preceding claim which is intended for use at a predetermined temperature wherein, the lattice parameter of aluminum solid solution matrix is within 1% of the lattice parameter of the Al_3X phase at the predetermined temperature.
5. A material as claimed in claim 4 wherein the lattice parameter of aluminum solid solution matrix is within 0.5% of the lattice parameter of the Al_3X phase at the predetermined temperature.
6. A material as claimed in claim 5 wherein the lattice parameter of aluminum solid solution matrix is within 0.25% of the lattice parameter of the Al_3X phase at the predetermined temperature.
7. A material as claimed in any preceding claim wherein said Al_3X phase is present in the form of particles and wherein

10% of said particles are less than 100 nm in diameter.

8. A material as claimed in any preceding claim wherein on an atomic basis, at least 10% of X is Sc.

5 9. A material as claimed in any preceding claim wherein on an atomic basis, at least 10% of X is Zr.

10. A material as claimed in any preceding claim on an atomic basis, less than 10% of X is Ti.

10 11. A material as claimed in any preceding claim wherein said Al_3X phase has a lattice parameter which is within 1% of the matrix lattice parameter at the intended use temperature.

12. A metal matrix composite containing a reinforcing second phase which comprises:

15 a) an aluminum alloy matrix which comprises an aluminum solid solution matrix containing a dispersion of Al_3X particles having a $L1_2$ crystal structure whose average size is less than about 250 nm, said matrix having a lattice parameter which is within 1% of the lattice parameter of the $L1_2Al_3X$ particles.

20 b) a reinforcing second phase whose geometry is selected from the group consisting of particles, fibers, woven fibers, braided fibers, fiber tows, particles, whiskers and ribbons and combinations thereof, and whose composition is selected from the group consisting of SiC, Si_3N_4 , Boron, Graphite, Al_2O_3 , BC and Y_2O_3 , $MgAl_2O_4$ said reinforcing second phase being present in an amount of from about 5 to about 20 vol%.

25 13. An aluminum alloy as in claim 12, comprising $L1_2$ particles in an aluminum solid solution matrix, wherein said alloy serves as a matrix to contain from about 5 to 60 vol. % of a reinforcing phase, wherein said reinforcing phase is selected from the group consisting of oxides, carbides, nitrides, carbonitrides, silicides, borides, boron, graphite, ferrous alloys, tungsten, and titanium and mixtures thereof; said reinforcing phase being non-coherent with said matrix alloy.

30

35

40

45

50

55

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 111 078 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
12.02.2003 Bulletin 2003/07

(51) Int Cl.7: **C22C 21/00, C22C 45/08**

(43) Date of publication A2:
27.06.2001 Bulletin 2001/26

(21) Application number: **00311378.4**

(22) Date of filing: **19.12.2000**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **22.12.1999 US 469858**

(71) Applicant: **UNITED TECHNOLOGIES
CORPORATION
Hartford, CT 06101 (US)**

(72) Inventor: **Watson, Thomas J.
South Windsor, Connecticut 06074 (US)**

(74) Representative: **Hall, Matthew Benjamin
Frank B. Dehn & Co.
179 Queen Victoria Street
London EC4V 4EL (GB)**

(54) **High strength aluminium alloy**

(57) A high strength dispersion strengthened aluminium alloy comprising an aluminum solid solution matrix strengthened by a dispersion of particles based on the compound Al_3X , where Al_3X has an $L1_2$ structure, is described. Various alloying elements are employed to

modify the lattice parameter of the matrix and/or the particles so that the matrix and particles have similar lattice parameters. The alloy is produced by rapid solidification from the melt.

EP 1 111 078 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 31 1378

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 5 226 983 A (SKINNER DAVID J ET AL) 13 July 1993 (1993-07-13) * column 3, line 62 - column 4, line 38 *	1-13	C22C21/00 C22C45/08
X	US 5 087 301 A (ANGERS LYNETTE M ET AL) 11 February 1992 (1992-02-11) * claims 1-16 *	1-13	
X	US 5 055 257 A (CHAKRABARTI DHRUBA J ET AL) 8 October 1991 (1991-10-08) * column 8, line 37 - column 9, line 41 *	1-13	
X	US 4 874 440 A (SAWTELL RALPH R ET AL) 17 October 1989 (1989-10-17) * column 8, line 35 - column 9, line 42 *	1-13	
A	RIDDLE, Y.W. (GEORGIA INSTITUTE OF TECHNOLOGY) ET AL: "Control of recrystallization in Al-Mg-Sc-Zr alloys." ALUMINIUM ALLOYS: THEIR PHYSICAL AND MECHANICAL PROPERTIES (1998), 1179-1184, NUMERICAL DATA, GRAPHS, PHOTOMICROGRAPHS, 11 REF. JAPAN INSTITUTE OF LIGHT METALS. TSUKAMOTO SOZAN BLDG., 6F, 4-2-15 GINZA, CHUO-KU, TOKYO, 104-0061, JAPAN CONFERENCE: ICAA, XP001118956 *Abstract*	1-13	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C22C
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 10 December 2002	Examiner Badcock, G
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/82 (P04001)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 31 1378

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	NORMAN, A.F. (UNIVERSITY OF MANCHESTER) ET AL: "The effect of scandium on the solidification behaviour of aluminium alloys." ALUMINIUM ALLOYS: THEIR PHYSICAL AND MECHANICAL PROPERTIES (1998), 219-224, PHASE DIAGRAMS, GRAPHS, PHOTOMICROGRAPHS, 14 REF. JAPAN INSTITUTE OF LIGHT METALS. TSUKAMOTO SOZAN BLDG., 6F, 4-2-15 GINZA, CHUO-KU, TOKYO, 104-0061, JAPAN CONFERENCE: ICAA-6, XP001118957 *Abstract*	1-13	
A	US 4 661 172 A (SKINNER DAVID J ET AL) 28 April 1987 (1987-04-28) * claims 1,6,12 *	1-13	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 10 December 2002	Examiner Badcock, G
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.92 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 31 1378

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

10-12-2002

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5226983 A	13-07-1993	AU 578828 B2	03-11-1988
		AU 5774986 A	30-01-1987
		CA 1280342 A1	19-02-1991
		DE 3665884 D1	02-11-1989
		EP 0229075 A1	22-07-1987
		JP 1008066 B	13-02-1989
		JP 62502295 T	03-09-1987
		NO 870903 A ,B,	04-03-1987
		WO 8700206 A1	15-01-1987
US 5087301 A	11-02-1992	NONE	
US 5055257 A	08-10-1991	US 4874440 A	17-10-1989
		US 4689090 A	25-08-1987
		CA 1287241 A1	06-08-1991
		FR 2595968 A1	25-09-1987
		GB 2188064 A ,B	23-09-1987
		JP 62284045 A	09-12-1987
US 4874440 A	17-10-1989	US 4689090 A	25-08-1987
		US 5055257 A	08-10-1991
		CA 1287241 A1	06-08-1991
		FR 2595968 A1	25-09-1987
		GB 2188064 A ,B	23-09-1987
		JP 62284045 A	09-12-1987
US 4661172 A	28-04-1987	CA 1228491 A1	27-10-1987
		DE 3562493 D1	09-06-1988
		EP 0158769 A1	23-10-1985
		JP 1613624 C	15-08-1991
		JP 2036661 B	20-08-1990
		JP 60208445 A	21-10-1985
		JP 1272742 A	31-10-1989

EPO FORM P0456

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82